

TOTAL SOLUTIONS®

DISPOSAL

Offer empty container for recycling. If recycling is not available, discard container in trash.

⚠ WARNING: This product can expose you to isobutyl methyl ketone, which is known to the State of California to cause cancer, and ethylene glycol, which is known to the State of California to cause birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov.

RUST CONVERTER

Stops, Converts, and
Inhibits Rust

- STOPS THE SPREAD OF RUST
- CONVERTS RUST TO A PAINTABLE SURFACE
- PROTECTS AGAINST FUTURE CORROSION
- NON-FUMING

KEEP OUT OF REACH OF CHILDREN

NET CONTENTS: One Quart (32 fl. oz.)

Manufactured By: Total Solutions®
PO Box 240014 • Milwaukee, WI 53224
1-800-743-6417



Please Recycle.

DESCRIPTION: This rust converter instantly bonds with rust, stops its growth, transforms it into a non-rusting paintable surface, and prevents future rust formation.

This rust converter provides an excellent primer coating for the application of quality oil-based paints. Surfaces protected with this primer and an oil-based paint system resist the effects of weather, rain, sun and salt spray without peeling or cracking. This easy-to-use product is the first step in providing long-term protection of steel and iron surfaces.

DIRECTIONS

SURFACE PREPARATION: Remove large rust and scale particles with a wire brush or sandpaper. Clean the surface thoroughly to remove dirt, dust and grease.

APPLICATION: Shake or stir well before using. This product is ready-to-use. Do not dilute. Apply this product using a brush or roller. Apply a second coat to ensure complete transformation of rusty surfaces.

COVERAGE: 500 square feet per gallon on a smooth, non-porous surface. Irregular, porous or textured surfaces may require more product.

DRYING TIME: The resulting coat will dry to a smooth, dark finish in 20 minutes. Apply a second coat to ensure complete transformation of rusty surfaces. Allow 48 hours of cure time before the application of the finished paint coat.

For long-lasting protection of iron surfaces, the cured rust converter should be sealed with two coats of a high quality oil-based paint. No other primer is required.

CLEAN-UP: Application equipment should be cleaned immediately with soap and water.

IMPORTANT: Do NOT return unused material to original containers.

NFPA® RATINGS: Health: 1; Flammability: 0; Reactivity: 0

CONTAINS/CAS NUMBER: Water/7732-18-5; Proprietary Polymer/Proprietary; 2-butoxyethanol/111-76-2; Tannic Acid/1401-55-4; Oxalic Acid/6153-56-6

0346.032018

*For industrial and commercial use only.
For additional information, see Safety Data Sheet.*